

Primabrite Ultra is a thin opaque offset paper specifically designed for the printing of pharmaceutical leaflets.

This paper provides the perfect compromise between whiteness and opacity.

Primabrite Ultra can be printed in either reels or sheets.

**FSC (BV-COC-051005-B) or PEFC (BV/CdC/2157457B) on request**

Characteristics	Unit	Standard	Spécifications				
			PBR37W30	PBR40W30	PBR45W30	PBR50W30	PBR60W30
Code							
Grammage	g/m <sup>2</sup>	ISO 536	37	40	45	50	60
Thickness	µm	ISO 534	48	52	59	65	78
Bulk	cm <sup>3</sup> /g	-	1.30	1.30	1.30	1.30	1.30
CIE whiteness	%	ISO 11475	130	130	130	130	130
Opacity	%	ISO 2471	78.5	80	80.5	81.5	85.5
pH paper	-	ISO 6588	8.5	8.5	8.5	8.5	8.5
Absolute humidity	%	NF Q03-003	5.8	5.8	5.8	5.8	5.8
Permanent paper	-	ISO 9706	OUI				
Optical brightner	-	-	OUI				
Luminescence			≥11	≥11	≥11	≥11	≥11
Fiber composition	%	NF Q01-007	100% Chemical Pulp : pure virgin fiber				

### Paper tolerances

Grammage: nominal value + / - 1 g/m <sup>2</sup>	CIE whiteness: minimum 125
Thickness: nominal value + / - 2 µm	Opacity minimum: nominal value - 1 point
Meets with REACH regulations	Suitable for food contact

### Finished goods tolerance

Joins: a maximum of 1 join per reel with a maximum 15% of the reels within any order containing joins. Joins are recorded on the delivery notes, on the reel label and also on the edge of the reel itself
Width: customer width - 0 mm, + 2 mm
Outer diameters of 100 cm, 114 cm or 120 cm: - 3 cm, + 2 cm

### Conditions of storage and optimal use

When in stock the paper should be stored in its original packaging and storage temperatures should not drop below <b>15 °C</b>
The paper should be acclimatized in the workshop area it's to be used, ideally <b>24</b> or even <b>48 hours</b> if possible before use
Optimal conditions of the workshop are: <b>23°C ±3°C</b> and <b>50% ±5%</b> of relative humidity

*Minimum making: Quantity required by the mill will be dependent on both the production schedules and the possibilities at the time of the order for a combination of widths to cover the machine deckle.*

*Please contact your sales representative for more details.*

Validated: 24/07/2019

Qualified by Emmanuel Bruneau-Technical Support Manager

Papeteries Des Vosges  
34 rue Maurice Mougeot  
88600 Laval Sur Vologne  
Tél : (33) 03 29 53 52 00  
Fax : (33) 03 29 53 52 01